



DuraForm® AF plastic

for use with all selective laser sintering (SLS®) systems

Polyamide (nylon) material with metallic appearance for real-world physical testing and functional use.



APPLICATIONS

- Housings and enclosures
- Consumer products
- Appropriate for low- to mid-volume rapid manufacturing
- Parts requiring machining or joining with adhesives
- Complex production and prototype plastic parts
- Form, fit or functional prototypes
- Parts requiring stiffness
- Thermally stressed parts
- Plastic parts requiring a metallic appearance

FEATURES

- Metallic appearance with nice surface finish
- Good powder recycle characteristics
- Excellent mechanical stiffness
- Easy-to-process
- Dimensionally stable

BENEFITS

- Excels in load bearing applications at higher temperatures
- Build prototypes and end-use parts without tooling
- Create accurate and repeatable parts as demanded by manufacturers
- Machinable for demonstration parts
- Improved isotropic shrinkage due to aluminum filler

PROTOFACTURING

TRANSFORM YOUR PRODUCTS

DuraForm® AF plastic

For use with all selective laser sintering (SLS®) systems

TECHNICAL DATA

General Properties

MEASUREMENT	METHOD/CONDITION	METRIC	U.S.
Specific Gravity	ASTM D792	1.42 g/cm ³	1.42 g/cm ³
Appearance	Visual	Light grey metallic	
Density (tap)	@ 25°C (77°F)	0.89 g/cm ³	0.89 g/cm ³
Density (bulk)	@ 25°C (77°F)	0.69 g/cm ³	0.69 g/cm ³

Mechanical Properties

MEASUREMENT	METHOD/CONDITION	METRIC	U.S.
Tensile Strength, Ultimate	ASTM D638	35 MPa	5060 psi
Tensile Modulus	ASTM D638	3960 MPa	574 ksi
Elongation at Break	ASTM D638	1.5 %	1.5%
Flexural Strength, Ultimate	ASTM D790	44 MPa	6290 psi
Flexural Modulus	ASTM D790	3517 MPa	510 ksi
Hardness, Shore D	ASTM D5420	75	75
Impact Strength (notched Izod, 23°C)	ASTM D256	58.7 J/m	1.1 ft-lbs/in
Impact Strength (unnotched Izod, 23°C)	ASTM D256	122.8 J/m	2.3 ft-lbs/in

Thermal Properties

MEASUREMENT	METHOD/CONDITION	METRIC	U.S.
Heat Deflection Temperature (HDT)	ASTM D648 @ 0.45 MPa	180 °C	356 °F
	@ 1.82 MPa	137 °C	279 °F
Coefficient of Thermal Expansion	ASTM E831 @ 35 - 172°C	109 µm/m-°C	60.5 µin/in-°F

Electrical Properties

MEASUREMENT	METHOD/CONDITION	METRIC	U.S.
Volume Resistivity	ASTM D257	1.6 x 10 ¹³ ohm-cm	1.6 x 10 ¹³ ohm-cm
Surface Resistivity	ASTM D257	6.0 x 10 ¹² ohm	6.0 x 10 ¹² ohm
Dielectric Constant, 1 KHz	ASTM D150	14.5	14.5
Dielectric Strength	ASTM D149	1.8 kV/mm	45.7 kV/in

Data was generated by building parts under typical default parameters. DuraForm AF plastic was processed on a base-level HiQ™ SLS system at 12 watts laser power, 200 inches/sec (5 m/sec) scan speed, and a powder layer thickness of 0.004 inches (0.1mm).



PROTOFACTURING

Protofacturing Group Inc.
3537 Ashby
Saint Laurent, QC, H4R 2K3
t: (514) 448-4220
f: (514) 866-0147

info@protofacturing.com
www.protofacturing.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. Protofacturing makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2007 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. HiQ and SinterScan are trademarks, and the 3D logo, DuraForm, Sinterstation and SLS are registered trademarks of 3D Systems, Inc.