

PPSF/PPSU (polyphenylsulfone) material has the greatest heat and chemical resistance of all Fortus materials - ideal for aerospace, automotive and medical applications. PPSF parts manufactured by Prototyping 3D Production are not only mechanically superior, but also dimensionally accurate, to better predict end-product performance. Users can also sterilize PPSF via steam autoclave, EtO sterilization, plasma sterilization, chemical sterilization and radiation⁵. PPSF gives you the ability to manufacture real parts directly from digital files that are ideal for conceptual modeling, functional prototyping, manufacturing tools, and end-use-parts.



Mechanical Properties ¹	Test Method	English	Metric
Tensile Strength (Type 1, 0.125", 0.2"/min)	ASTM D638	8,000 psi	55 MPa
Tensile Modulus (Type 1, 0.125", 0.2"/min)	ASTM D638	300,000 psi	2,068 MPa
Tensile Elongation (Type 1, 0.125", 0.2"/min)	ASTM D638	3%	3%
Flexural Strength (Method 1, 0.05"/min)	ASTM D790	15,900 psi	110 MPa
Flexural Modulus (Method 1, 0.05"/min)	ASTM D790	320,000 psi	2,206 MPa
IZOD Impact, notched (Method A, 23°C)	ASTM D256	1.1 ft-lb/in	58.73 J/m
IZOD Impact, un-notched (Method A, 23°C)	ASTM D256	3.1 ft-lb/in	165.5 J/m

Thermal Properties ³	Test Method	English	Metric
Heat Deflection (HDT) @ 264 psi	ASTM D648	372°F	189°C
Glass Transition Temperature (Tg)	DMA (SSYS)	446°F	230°C
Coefficient of Thermal Expansion	ASTM D696	3.1 E -05 in/in/°F	5.5 E -05 mm/mm/°C
Melt Point	-----	Not Applicable ²	Not Applicable ²

Other ³	Test Method	Value
Specific Gravity	ASTM D792	1.28
Flame Classification	UL 94	V0 (0.126", 3.2 mm)
Rockwell Hardness	ASTM D785	M86
Dielectric Strength	IEC 60112	14.6 kV/mm
Dielectric Constant @ 60 Hz	IEC 60250	3.45

Environmental Resistance ⁴	24 hours @ 23°C (73°F)	24 hours @ 100°C (212°F)
Antifreeze (Prestone), 50%	Passed	Passed
Gasoline-Unleaded	Passed	Not tested
Motor Oil 10W-40	Passed	Passed
Power Steering Fluid	Passed	Passed
Transmission Fluid	Passed	Passed
Windshield Washer Fluid, 50%	Passed	Not tested

► See reverse for color options and system availability.

The information presented are typical values intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, etc. Actual values will vary with build conditions. Tested parts were built on 400mc @ 0.010" (0.254 mm) slice. Product specifications are subject to change without notice.

¹ Build orientation is on side long edge. ² Due to amorphous nature, material does not display a melting point. ³ Literature value unless otherwise noted. ⁴ Test results based on Stress Crack Resistance (24-hour immersion @ 23°C and @ 100°C). ⁵ Stratays has not done any sterilization testing on PPSF.



System Availability	Layer Thickness Capability	Support Structure	Available Colors
400mc	0.013 inch (0.330 mm) 0.010 inch (0.254 mm)	BASS	■ Tan

At the core: Advanced FDM[®] technology

FDM — Fused Deposition Modeling — technology. FDM is the industry's leading additive fabrication technology, and the only one that uses production grade thermoplastics, enabling the most durable parts.

Our systems use a wide range of thermoplastics with advanced mechanical properties so your parts can endure high heat, caustic chemicals, sterilization, and high impact applications.

Get your benchmark on the future of manufacturing

Fine details. Smooth surface finishes. Accuracy. Strength. The best way to see the advantages of a Prototyping 3D production is to have your own part built by us. Call today

For more information about Prototyping 3D production, materials and applications, call **514.448.4220** or visit **www.prototyping.com**

Prototyping Group Inc

3537 Ashby
Saint-Laurent, QC, H4R 2K3
514 448 4220
514 866 0147 (Fax)
www.prototyping.com
info@prototyping.com



prototyping
prototyping